



## PENPET PETROCHEMICAL TRADING HAMBURG

**MERKUR PARK**  
Sieker Landstr. 126  
D-22143 Hamburg  
Germany

**FAX-No. (+) 49 40 675 799-99/88**  
**TEL-No. (+) 49 40 675 799-0**  
**e-mail: info@penpet.de**  
**Internet: www.penpet.de**

---

### SPECIFICATION

---

**Product: Maleic Anhydride (MA) liquid**

---

| CHARACTERISTICS      | UNITS | MIN. / MAX. VALUES |
|----------------------|-------|--------------------|
| Purity               | %     | min. 99.6          |
| Colour               | APHA  | max. 20            |
| Solidification Point | °C    | min. 52.5          |
| Solution in Xylene   | --    | clear              |
| Iron                 | ppm   | max. 1             |
| Ash                  | ppm   | max. 10            |

**Packing: heated in tank-truck**

Source: [www.penpet.de](http://www.penpet.de)

While Penpet undertakes reasonable efforts to offer accurate, complete and up-to-date information, Penpet is not responsible for and disclaims any liability for any damages, including without limitation, direct, indirect, incidental, consequential and special damages, alleged to have been caused by or in connection with the access and/ or use of this information.